

(19)

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 186 644 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
13.03.2002 Bulletin 2002/11

(51) Int Cl.7: **C09J 153/02, C09J 7/02**

(21) Application number: **01120481.5**

(22) Date of filing: **28.08.2001**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

- Sasaki, Yasuyuki, c/o Nitto Denko Corporation
Ibaraki-shi, Osaka (JP)
- Kasahara, Tsuyoshi,
c/o Nitto Denko Corporation
Ibaraki-shi, Osaka (JP)

(30) Priority: **28.08.2000 JP 2000257690**

(74) Representative: **Grünecker, Kinkeldey,
Stockmair & Schwanhäusser Anwaltssozietät
Maximilianstrasse 58
80538 München (DE)**

(71) Applicant: **NITTO DENKO CORPORATION
Osaka (JP)**

(72) Inventors:
• **Kuniya, Masayoshi, c/o Nitto Denko Corporation
Ibaraki-shi, Osaka (JP)**

(54) **Pressure-sensitive adhesive composition and pressure-sensitive tape or sheet**

(57) A pressure-sensitive adhesive composition comprises: 100 parts by weight of a rubber component that is solid in an ordinary temperature; 30 to 170 parts by weight of a rubber component that is liquid in an ordinary temperature; and 50 to 400 parts by weight of a

tackifier, wherein the amount of the tackifier is 25 to 80 parts by weight based on 100 parts by weight of the total amount of the rubber components.

EP 1 186 644 A2

Description**BACKGROUND OF THE INVENTION**

5 1. FIELD OF THE INVENTION

10 [0001] The present invention relates to a pressure-sensitive adhesive composition, and a pressure-sensitive adhesive tape or sheet using the same. More specifically, it relates to a pressure-sensitive adhesive composition, and a pressure-sensitive adhesive tape or sheet to be used optimally for the external application in the field of medical hygiene, sports, and the beauty and health, as a first aid adhesive tape, a large size adhesive plaster, or a dressing material.

2. DESCRIPTION OF THE RELATED ART

15 [0002] In a pressure-sensitive adhesive composition provided for the application in a form of a pressure-sensitive adhesive tape or sheet, the adhesive property with respect to an adherend, the adhesive property (anchoring property) with respect to a backing film surface, and the cohesive property in a pressure-sensitive adhesive layer should be balanced. By balancing the same, quick contact and adhesion to an adherend can be enabled as well as the pressure-sensitive adhesive tape or sheet can be peeled off at the time of peeling and removing the same from the adherend neatly without the so-called adhesive residue phenomenon of leaving the pressure-sensitive adhesive on the surface of the adherend.

20 [0003] Moreover, the pressure-sensitive adhesive composition can be, in general, divided into an acrylic based adhesive and a rubber based adhesive on the whole. The acrylic based adhesive can be obtained by polymerization of an acrylic acid ester based monomer used as the main component monomer. Since a pressure-sensitive adhesive composition can be obtained according to the demanded characteristics, it is used widely.

25 [0004] In contrast, the rubber based adhesive can be divided into a natural rubber based one and a synthetic rubber based one on the whole. Compared with the acrylic based adhesive, it has a superior adhesive property. Moreover, it can be produced easily only by mixing materials as well as it has a relatively good reproductivity.

30 [0005] Such a rubber based adhesive, in general, comprises a rubber component and a tackifier as the main component, and optionally other materials such as a softening agent and a filler. That is, a pressure-sensitive adhesive composition is provided by adding a tackifier having a high glass transition temperature to the rubber component, which has a glass transition temperature of an ordinary temperature or less so as to adjust the glass transition temperature of the entire product to a temperature slightly lower than the actual use temperature.

35 [0006] However, since the pressure-sensitive adhesive tape or sheet is used in various fields. In particular, in the case of the medical application, the beauty and health application, the sports application, or the like, since the adherend is a skin surface, strict conditions are applied to the demanded characteristics compared with the case of a pressure-sensitive adhesive tape or sheet to be bonded on a surface other than an organism surface. That is, since the skin surface state differs individually, the bonding state differs largely for a person with dry skin and a person with oily skin even in the case the same adhesive tape or sheet is used. Moreover, it differs also depending on the attachment position. In the case of attaching on a bending part such as an elbow or knee joint, or on a finger, a higher skin adhesive property is required. Furthermore, the excellent adhesive property with respect to bathing, kitchen work, perspiration, or the like (water proof adhesive property) is required as well as adjustment is necessary so as not to fluctuate the adhesive force in a low temperature of winter. That is, since the pressure-sensitive adhesive tape or sheet to be attached on the skin surface is used in most cases in a severer condition with respect to an ordinary adhesive tape or sheet, development of a pressure-sensitive adhesive composition having a higher adhesive force, capable of satisfying the need is keenly called for.

45 [0007] As a method for improving the adhesive force and the adhesion force, addition of a tackifier can be presented. However, in the case the tackifier is contained by a large amount, the glass transition temperature of the entire product is raised as mentioned above so that the adhesion force tends to be lowered in a low temperature. Moreover, since the tackifier has a relatively low molecular weight of several hundreds to several thousands, in the case it is contained by a large amount, it may be bloomed from a pressure-sensitive adhesive layer and transferred into a backing film so as to wet the backing film and generate wrinkles in the film.

50 [0008] In contrast, JP-W-8-506127 (published Japanese translation of PCT International publication) discloses a proposal for balancing the adhesion characteristic without containing a tackifier. It is for maintaining the adhesion characteristic only with a rubber component that is solid in an ordinary temperature and a liquid rubber component without containing a tackifier. By containing the liquid rubber component instead of the tackifier, the entire product is plasticized so as to lower the glass transition temperature, and improve the adhesive property with respect to an adherend. However, the cohesive force in the pressure-sensitive adhesive layer tends to be lowered, and it becomes too

soft in an ordinary temperature. Therefore, for example, cohesive failure, adhesion residue of the pressure-sensitive adhesive component remained on an adherend, or the like are generated. Accordingly, a pressure-sensitive adhesive composition having a relatively sticky feeling is provided.

5 SUMMARY OF THE INVENTION

[0009] In order to solve the problems of the related art, the invention has been achieved. An object thereof is to provide a pressure-sensitive adhesive composition with the adhesive force, the cohesive force, and the anchoring force balanced, having the excellent low temperature characteristic and water proof characteristic, without the problem of the sticky feeling in the conventional rubber based adhesives, without the risk of swelling a backing film, and a pressure-sensitive adhesive tape or sheet using the same.

[0010] As a result of the elaborate discussion of the present inventors for achieving the object, it was found out that a pressure-sensitive adhesive composition having the excellent adhesion characteristic, which is not found in the conventional rubber based adhesives can be obtained by containing a rubber component that is solid in an ordinary temperature, a liquid rubber component, and a tackifier by a specific composition ratio so that the invention has been completed.

[0011] That is, the invention is to provide a pressure-sensitive adhesive composition containing 30 to 170 parts by weight of a rubber component that is liquid in an ordinary temperature (e.g., 25°C), and 50 to 400 parts by weight of a tackifier with respect to 100 parts by weight of a rubber component that is solid in an ordinary temperature (e.g., 25°C), wherein the tackifier is contained in a range of 25 to 80 parts by weight with respect to 100 parts by weight of the total rubber component amount.

[0012] Moreover, the invention is to provide a pressure-sensitive adhesive tape or sheet comprising the pressure-sensitive adhesive composition according laminated on one side of a backing film.

25 DETAILED DESCRIPTION OF THE INVENTION

[0013] A pressure-sensitive adhesive composition according to the invention contains a rubber component that is solid in an ordinary temperature, a rubber component that is liquid in an ordinary temperature, and a tackifier as the essential components. The effect of the invention cannot be performed without any of the components.

[0014] The rubber component that is solid in an ordinary temperature to be used in the invention serves as a base polymer for a pressure-sensitive adhesive composition. For example, an A-B type block copolymer, an A-B-A type block copolymer, or the like can be used. As the A-B type block copolymer, specifically, block copolymers such as a styrene-butadiene block copolymer, and a styrene-isoprene block copolymer can be used. A block copolymer used in the invention is preferably a linear block copolymer. It is not preferable to use a radial block copolymer because it has a high cohesive force compared with a linear block copolymer so that in the case it is used as a pressure-sensitive adhesive, it is inferior in terms of tacking and wettability with respect to the adherend.

[0015] Moreover, among the A-B type block copolymers and the A-B-A type block copolymers, it is preferable to use the styrene/isoprene block copolymer, and the styrene/isoprene/styrene block copolymer rather than the other rubbers solid in an ordinary temperature because the cohesive force and the elastic modulus can be balanced easily so as to facilitate designing of the pressure-sensitive adhesive as well as processing. In particular, those having a 10 to 20% by weight styrene unit content and a weight average molecular weight of 80,000 to 300,000 can be used preferably.

[0016] Furthermore, in the case a styrene/isoprene/styrene block copolymer is used, it is preferable to use a mixture containing a styrene/isoprene copolymer as a diblock copolymer by 60 to 90% by weight rather than one containing a styrene/isoprene/styrene block copolymer by 100% in terms of tacking and wettability with respect to the adherend.

[0017] Moreover, as a rubber component that is liquid in an ordinary temperature used in the invention, those compatible with the solid rubber component, such as a liquid polyisoprene and a derivative thereof, a liquid polybutadiene, a liquid polyisobutylene, a liquid polybutene, a liquid styrene-isoprene copolymer, a liquid isoprene-butadiene copolymer, or the like can be presented. They can be used alone or in a combination of two or more.

[0018] As the liquid rubbers, those having about a 10,000 to 100,000, preferably 20,000 to 60,000 weight average molecular weight can be used preferably in order to prevent transfer to a backing film comprising a pressure-sensitive adhesive tape or sheet.

[0019] In the invention, according to a pressure-sensitive adhesive composition containing the solid rubber and liquid rubber, the low temperature characteristic can be improved. However, since the adhesion characteristic involves a slight problem in an ordinary temperature region, a tackifier is contained. As such a tackifier, natural resins of terpene based, rosin based, or a derivative thereof, and synthetic resins of aliphatic group based, aromatic group based, petroleum resin based, alkyl phenol based, xylene based, or coumarone indene based, or the like can be used. They can be used alone or in a combination of two or more.

[0020] The tackifier, which is homogeneously compatible with the solid rubber and liquid rubber components, is for

improving the adhesion characteristic in an ordinary temperature and preventing the sticky feeling. The number average molecular weight of such a tackifier is about 500 to 2,000, preferably 600 to 1,500 for providing a good compatibility and preventing transfer to a backing film.

[0021] Furthermore, in order to prevent transfer of the tackifier to the backing film, it is preferable to strictly administer the SP value (solubility parameter) of the tackifier, and it is preferable to adopt a tackifier having an SP value away from that of the backing film. Specifically, the kind of the tackifier to be used can be selected optionally according to the combination with the backing film, but for example, in the case an olefin based backing film is used, as the tackifier, a terpene based natural resin can be used preferably.

[0022] A pressure-sensitive adhesive composition according to the invention contains the rubber component that is solid in an ordinary temperature, the rubber component that is liquid in an ordinary temperature, and the tackifier by a specific ratio. According to the composition ratio, the targeted object can be achieved. Specifically, 30 to 170 parts by weight, preferably 40 to 115 parts by weight of the rubber component that is liquid in an ordinary temperature, and 50 to 400 parts by weight, preferably 60 to 150 parts by weight of the tackifier are contained with respect to 100 parts by weight of the rubber component that is solid in an ordinary temperature as well as the tackifier is contained in a range of 25 to 80 parts by weight, preferably 40 to 70 parts by weight with respect to 100 parts by weight of the total amount of the rubber components.

[0023] In the case the amount of the liquid rubber component is small, it is difficult to improve the pressure-sensitive adhesion characteristic in a low temperature. In contrast, in the case the amount is too large, the cohesive force is lowered so that adhesive residue or generation of sticky feeling on the skin surface tend to occur.

[0024] Moreover, in the case the amount of the tackifier with respect to the solid rubber component is too small, an adhesive property superior to that of the conventional rubber based adhesive can hardly be provided. In contrast, in the case the amount is too large, the glass transition temperature of the entire adhesive becomes high so that the adhesive property at an ordinary temperature tends to be lowered. Furthermore, it is necessary to adjust the amount of the tackifier in the range with respect to the rubber component total amount. If it is less than 25 parts by weight with respect to the rubber component total amount, it is difficult to provide an adhesive property superior to that of the conventional rubber based adhesive. In contrast, if it is more than 80 parts by weight, the adhesive property under an ordinary temperature is lowered, and further, the agent can easily transfer to the backing film so as to swell the film.

[0025] A pressure-sensitive adhesive composition according to the invention is made of the essential components. In the range not to deteriorate the adhesion characteristic, a cross-linking agent, an antioxidant, a heat stabilizing agent, a pigment, an ultraviolet ray absorbing agent, a filler, or the like can be contained optionally.

[0026] A pressure-sensitive adhesive tape or sheet (hereinafter referred to as adhesive tapes) according to the invention is provided by forming the pressure-sensitive adhesive composition on one side of a backing film like a layer. The backing film can be obtained from materials such as urethane based polymers including a polyether urethane, and a polyester urethane, amide based polymers including a polyether polyamide blockpolymer, acrylic based polymers including a polyacrylate, polyolefin based polymers including a polyethylene, a polypropylene, an ethylene/propylene copolymer, and an ethylene/vinyl acetate copolymer, polyester based polymers including a polyether polyester, a vinyl chloride, a vinylidene chloride, a polystyrene, a polyacrylonitrile, a polycarbonate, a polyimide, or the like. Among these examples, it is preferable to use an olefin based backing film since it has a low risk of generating a dioxin at the time of incineration, it has the excellent feeling including the flexibility, it has a sufficient mechanical strength in the practical use, and it is excellent in terms of the cost performance. It is particularly preferable to use an ethylene/vinyl acetate copolymer, an ethylene/propylene copolymer, and an ethylene/methacrylic acid copolymer. The backing film can be made of either one of the materials, or can be a laminated film having a plurality of films of an optional material laminated.

[0027] The thickness of the backing film is preferably about 30 to 200 μm , preferably 40 to 150 μm in order not to generate a strange feeling at the time of attaching on the skin surface. Moreover, it is preferable to adjust the 50% modulus (stress at the time of stretching by 50%) to about 1×10^6 to 1×10^7 Pa, and the tensile strength to about 1×10^6 to 9×10^7 Pa in order to have a good skin followability at the time of attaching on the skin as well as to provide a strength satisfactory for the practical use. By using a backing film adjusted in the ranges, the excellent skin followability at the time of attaching on the skin surface with a large movement such as a joint portion can be provided as well as the film can be removed without being torn at the time of peeling off, and thus it is effective.

[0028] The backing film is not limited to a non-porous film, but it is also effective to use a vapor transmissible, non-water permeable porous film in terms of prevention of stuffiness during attachment. In the case of such a film, the material is not particularly limited, and it can be obtained easily by applying a known technique for the porosity treatment. In the case of a non-porous film, tendency of decline of the vapor transmissibility is found remarkably. However, since decline of the vapor transmissibility is not found remarkably in the case of a porous film, it is useful.

[0029] The thickness of the pressure-sensitive adhesive layer to be formed on the backing film is preferably about 15 to 100 μm . In the case it is less than 15 μm , a sufficient skin adhesive property may not be provided at the time of attaching on the skin. In contrast, in the case it is more than 100 μm , protrusion of the pressure-sensitive adhesive or cost increase may be brought about.

[0030] An attaching material for the medical treatment according to the invention can be used preferably in a first aid adhesive tape, a large size adhesive plaster, a roller bandage, a dressing material, or the like. According to the application thereof, for example, in the case of an adhesive plaster having a relatively large thickness (the thickness is, in general, about 100 μm), it is preferable to use a porous film. As a base material film preferable for the porous film, a porous plastic film made of a polyolefin based resin can be presented. For example, resins such as a polyethylene, a polypropylene, and an ethylene-vinyl acetate copolymer can be used. In particular, a linear low density polyethylene resin can be used preferably in terms of the productivity and the processability. The linear low density polyethylene resin is a copolymer of an ethylene and an α -olefin. As the α -olefin, a butene, a hexene, an octene, or the like can be presented.

[0031] Adhesive tapes according to the invention have the configuration. In general, a peeling sheet treated with a peeling process such as a silicone process on the surface is attached temporarily on the exposed surface of the pressure-sensitive adhesive layer.

[0032] A pressure-sensitive adhesive composition and a pressure-sensitive adhesive tape or sheet using the same according to the invention provide the excellent adhesion characteristic under an ordinary temperature, which is not found in the conventional rubber based adhesives, by containing a solid rubber component, a liquid rubber component, and a tackifier by a specific ratio, and the excellent maintenance of the adhesion characteristic under a low temperature, and thus they can be used preferably for the application having the skin surface as the adherend.

[0033] In particular, since the pressure-sensitive adhesive composition according to the invention contains the components by the specific ratio, a tackifier may not be bloomed and transferred into a backing film so that adhesive tapes with the excellent practicality can be obtained without the risk of generating wrinkles in the backing film.

EXAMPLES

[0034] Hereinafter, the invention will be described further specifically with reference to examples, but the invention is not limited thereto, and various modifications can be performed without departing from the scope of the technological idea of the invention. In the description below, a "part" denotes a "part by weight", and "%" denotes "% by weight".

Example 1

[0035] A solution of a pressure-sensitive adhesive composition was produced by dissolving 100 parts of a styrene/isoprene/styrene block copolymer (styrene content: 15%, weight average molecular weight: 188,000, diblock content: 78%), 40 parts of a liquid polyisoprene (weight average molecular weight 29,000), and 60 parts of a β -pinene (number average molecular weight: 1,350, softening point: 115°C) in a toluene so as to have a 55% solid component concentration.

[0036] Next, the pressure-sensitive adhesive solution was applied and dried on the processed surface side of a separator treated with a silicone process on one side so as to have a 40 μm thickness after drying so as to form a pressure-sensitive adhesive layer.

[0037] Then, the produced adhesive layer was attached on an ethylene/vinyl acetate copolymer film (100 μm thickness) so as to provide a pressure-sensitive adhesive sheet according to the invention.

Example 2

[0038] A solution of a pressure-sensitive adhesive composition was produced by dissolving 100 parts of a styrene/isoprene/styrene block copolymer (same as the example 1), 115 parts of a liquid polyisoprene (same as the example 1), and 150 parts of a β -pinene (same as the example 1) in a toluene so as to have a 55% solid component concentration.

[0039] Next, the pressure-sensitive adhesive solution was applied and dried on the processed surface side of a separator treated with a silicone process on one side so as to have a 40 μm thickness after drying so as to form a pressure-sensitive adhesive layer.

[0040] Then, the produced adhesive layer was attached on an ethylene/vinyl acetate copolymer film (100 μm thickness) so as to provide a pressure-sensitive adhesive sheet according to the invention.

Comparative Example 1

[0041] A pressure-sensitive adhesive sheet was produced in the process same as that of the example 1 except that a pressure-sensitive adhesive composition solution was produced by dissolving 100 parts of a styrene/isoprene/styrene block copolymer (same as the example 1), 115 parts of a liquid paraffin, and 150 parts of a β -pinene (same as the example 1) in a toluene so as to have a 55% solid component concentration.

Comparative Example 2

5 [0042] A pressure-sensitive adhesive sheet was produced in the process same as that of the example 1 except that a pressure-sensitive adhesive composition solution was produced by dissolving 100 parts of a styrene/isoprene/styrene block copolymer (same as the example 1), and 150 parts of a β -pinene (same as the example 1) in a toluene so as to have a 55% solid component concentration.

Comparative Example 3

10 [0043] A pressure-sensitive adhesive sheet was produced in the process same as that of the example 1 except that a pressure-sensitive adhesive composition solution was produced by dissolving 100 parts of a styrene/isoprene/styrene block copolymer (same as the example 1), and 115 parts of a liquid polyisoprene (same as the example 1) in a toluene so as to have a 55% solid component concentration.

15 Comparative Example 4

[0044] A pressure-sensitive adhesive sheet was produced in the process same as that of the example 1 except that a pressure-sensitive adhesive composition solution was produced by dissolving 100 parts of a styrene/isoprene/styrene block copolymer (styrene content: 15%, diblock content: 40%), and 300 parts of a liquid polyisoprene (same as the example 1) in a toluene so as to have a 55% solid component concentration.

Comparative Example 5

25 [0045] A pressure-sensitive adhesive sheet was produced in the process same as that of the example 1 except that a pressure-sensitive adhesive composition solution was produced by dissolving 100 parts of a styrene/isoprene/styrene block copolymer (same as the comparative example 4), and 300 parts of a liquid polyisoprene (weight average molecular weight: 47,000) in a toluene so as to have a 55% solid component concentration.

Comparative Example 6

30 [0046] A pressure-sensitive adhesive sheet was produced in the process same as that of the example 1 except that a pressure-sensitive adhesive composition solution was produced by dissolving 100 parts of a styrene/isoprene/styrene block copolymer (same as the example 1), 250 parts of a liquid polyisoprene (same as the example 1), and 150 parts of a β -pinene (same as the example 1) in a toluene so as to have a 55% solid component concentration.

35 Comparative Example 7

[0047] A pressure-sensitive adhesive sheet was produced in the process same as that of the example 1 except that a pressure-sensitive adhesive composition solution was produced by dissolving 100 parts of a styrene/isoprene/styrene block copolymer (same as the example 1), 115 parts of a liquid polyisoprene (same as the example 1), and 500 parts of a β -pinene (same as the example 1) in a toluene so as to have a 55% solid component concentration.

[0048] The pressure-sensitive adhesive sheets obtained in the examples and the comparative examples were evaluated for the skin adhesive force, the tacking, and the backing film swelling property by the following methods. Results are shown in the table 1.

45 <Skin Adhesive force>

[0049] The pressure-sensitive adhesive sheets produced in the examples and the comparative examples were cut into a strip-like shape of a 19 mm width and a 100 mm length. The strips were pressed on a human skin arm part by a 2 kg roller by one reciprocal movement at about a 50 mm/second rate under a $23 \pm 2^\circ\text{C}$, relative humidity $65 \pm 15\%$ environment. After leaving for 30 minutes, the pressure-sensitive adhesive sheets were peeled off by a 90 degree peeling angle, and a 300 mm/minute peeling rate. The peeling stress applied at the time was defined to be the skin adhesive force. The skin surface was observed after the peeling operation for examining existence or absence of the sticky feeling derived from the adhesive residue on the skin surface at the same time.

55 <Tacking>

[0050] The backing film side of the pressure-sensitive adhesive sheets produced in the examples and the compar-

EP 1 186 644 A2

ative examples was lined with a polypropylene adhesive tape (produced by Nitto Denko Corp., Danpuron Tape No. 375). With a probe tack tester (produced by Rigaku Kogakusha Corp.), the stress at the time of peeling off a 5 mm diameter stainless steel probe from the pressure-sensitive adhesive layer surface by a 100 g pressure load, 1 second contact time, and 10 mm/second peeling rate condition was measured under a $23 \pm 2^{\circ}\text{C}$, relative humidity $65 \pm 15\%$ environment. The value thereof was defined to be the tacking value.

<Backing Film Swelling Property>

[0051] The pressure-sensitive adhesive sheets produced in the examples and the comparative examples were cut into a 100 mm square rectangular shape. After leaving at 50°C for 3 days, the appearance of the backing film was judged by the following judgment standard.

A: Swelling or wrinkles are not generated on the backing film.

B: Slight swelling is observed on the backing film.

C: Swelling and wrinkles are generated apparently on the backing film.

TABLE I

	Example		Comparative example						
	1	2	1	2	3	4	5	6	7
Skin adhesion force (N/19mm)	2.7	3.8	3.5	0.2	2.0	0.7	1.0	3.0	0.1
Sticky feeling	No	No	Yes	No	Yes	Yes	Yes	Yes	No
Tacking (N/5mm diameter)	9.5	9.5	6.5	0.1	4.3	3.4	2.4	5.7	0.1
Backing film swelling property	A	A	C	A-B	A	A	A	A	B

[0052] As it is apparent from the results of the table 1, the products of the examples show the excellent results in all items of the evaluation. In particular, as it is apparent from the results of the products of the examples containing a liquid rubber and the product of the comparative example 1 containing a liquid paraffin instead of a liquid rubber, according to the invention, the backing film is not swelled without the risk of adhesive residue on the skin surface, which is the adherend.


[0053] Moreover, as it is apparent from the results of the products of the examples containing a liquid rubber and the product of the comparative example 2 not containing a liquid rubber, the products of the invention are superior to the products of the comparative examples in all the items including the skin adhesive force, the tacking, and the backing film swelling property. They are apparently well-balanced adhesive sheets.

[0054] Furthermore, as it is apparent from the results of the products of the examples containing a tackifier and the products of the comparative examples 3 to 5 not containing a tackifier, the products of the comparative examples are slightly poor in terms of the skin adhesive force and the tacking, and they provide the sticky feeling derived from the adhesive residue on the skin surface, which is the adherend.

[0055] The entire disclosure of each and every foreign patent application from which the benefit of foreign priority has been claimed in the present application is incorporated herein by reference, as if fully set forth herein.

Claims

1. A pressure-sensitive adhesive composition comprising: 100 parts by weight of a rubber component that is solid in an ordinary temperature; 30 to 170 parts by weight of a rubber component that is liquid in an ordinary temperature; and 50 to 400 parts by weight of a tackifier, wherein the amount of the tackifier is 25 to 80 parts by weight based on 100 parts by weight of the total amount of the rubber components.
2. The pressure-sensitive adhesive composition according to claim 1, wherein the rubber component that is solid in an ordinary temperature is at least one of an A-B block copolymer and an A-B-A block copolymer.
3. The pressure-sensitive adhesive composition according to claim 1, wherein the rubber component that is liquid in an ordinary temperature is at least one selected from the group consisting of a liquid polyisoprene and a derivative thereof, a liquid polybutadiene, a liquid polyisobutylene, a liquid polybutene, a liquid styrene-isoprene copolymer, and a liquid isoprene-butadiene copolymer.
4. The pressure-sensitive adhesive composition according to claim 1, wherein the tackifier is at least one selected from the group consisting of: natural resins of a terpene resin and a rosin resin or a derivative thereof; and synthetic resins of an aliphatic resin, an aromatic resin, a petroleum resin, an alkyl phenol resin, a xylene resin, and a coumarone indene resin.
5. A pressure-sensitive adhesive tape or sheet comprising a pressure-sensitive adhesive composition according to claim 1 formed on one side of a backing film.
6. The pressure-sensitive adhesive tape or sheet according to claim 5, wherein the backing film is an olefin film.
7. The pressure-sensitive adhesive tape or sheet according to claim 6, wherein the olefin film is one selected from the group consisting of an ethylene/vinyl acetate copolymer film, an ethylene/(meth)acrylic acid copolymer film, an ethylene/methyl (meth)acrylate copolymer film, an ethylene/ethyl (meth)acrylate copolymer film, an ethylene/vinyl alcohol copolymer film, and an ethylene/propylene copolymer film, or a laminated product thereof.
8. The pressure-sensitive adhesive composition according to claim 1, wherein the amount of the rubber component that is liquid in an ordinary temperature is 40 to 115 parts by weight based on 100 parts by weight of the rubber component that is solid in an ordinary temperature.
9. The pressure-sensitive adhesive composition according to claim 1, wherein the amount of the tackifier is 40 to 70 parts by weight based on 100 parts by weight of the total amount of the rubber components.



(19)

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 186 644 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
19.03.2003 Bulletin 2003/12

(51) Int Cl.7: **C09J 153/02**, C09J 7/02,
C09J 109/00, C09J 121/00,
C09J 115/00

(43) Date of publication A2:
13.03.2002 Bulletin 2002/11

(21) Application number: **01120481.5**

(22) Date of filing: **28.08.2001**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

- Sasaki, Yasuyuki, c/o Nitto Denko Corporation
Ibaraki-shi, Osaka (JP)
- Kasahara, Tsuyoshi,
c/o Nitto Denko Corporation
Ibaraki-shi, Osaka (JP)

(30) Priority: **28.08.2000 JP 2000257690**

(74) Representative: **Grünecker, Kinkeldey,
Stockmair & Schwanhäusser Anwaltssozietät
Maximilianstrasse 58
80538 München (DE)**

(71) Applicant: **NITTO DENKO CORPORATION
Osaka (JP)**

(72) Inventors:
• **Kuniya, Masayoshi, c/o Nitto Denko Corporation
Ibaraki-shi, Osaka (JP)**

(54) Pressure-sensitive adhesive composition and pressure-sensitive tape or sheet

(57) A pressure-sensitive adhesive composition comprises: 100 parts by weight of a rubber component that is solid in an ordinary temperature; 30 to 170 parts by weight of a rubber component that is liquid in an ordinary temperature; and 50 to 400 parts by weight of a

tackifier, wherein the amount of the tackifier is 25 to 80 parts by weight based on 100 parts by weight of the total amount of the rubber components.

EP 1 186 644 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 12 0481

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	EP 0 285 181 A (TEIKOKU SEIYAKU KK) 5 October 1988 (1988-10-05) * abstract : page 3, line 35-45 ; page 3, line 51 - page 4, line 2 ; page 4, line 15-16 ; page 4, line 40-48 ; claims 1-4 ; examples *	1-9	C09J153/02 C09J7/02 C09J109/00 C09J121/00 C09J115/00
X	US 5 760 135 A (KORPMAN DENNIS ET AL) 2 June 1998 (1998-06-02) * claims 9, 10, 11 ; column 5, line 5-8 ; claims 1-13 ; column 5, line 8-48 ; column 2, line 55-56 * * abstract *	1-4,8,9	
P,X	EP 1 043 373 A (NITTO DENKO CORP) 11 October 2000 (2000-10-11) * Example 2 ; page 4, line 14-18 ; page 4, line 25-34 ; page 3, line 26-33, 24-25, 54-58 ; claims 1-8 ; abstract * * abstract *	1-9	
X	DE 42 07 65/ A (TAKEDA CHEMICAL INDUSTRIES LTD) 17 September 1992 (1992-09-17) * abstract : claims 1, 23, 24, 7, 8, 9, 27 ; page 5, line 35-42 * * page 3, line 2-4 ; examples 1-3 *	1-5,8,9	
Y		6,7	C09J C08L A61F A61K
X	US 4 551 490 A (DOYLE ARTHUR ET AL) 5 November 1985 (1985-11-05) * abstract : claims 1,3,4,5,6,7,10,12-25 ; examples * * column 6, line 12-15 *	1-5,8,9	
-/-			
The present search report has been drawn up for all claims.			
Place of search		Date of completion of the search	Examiner
THE HAGUE		16 January 2003	Hammond, A
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : oral-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application I : document cited for other reasons S : member of the same patent family corresponding document</p>			



European Patent
Office

Application Number
EP 01 12 0481

CLAIMS INCURRING FEES

The present European patent application comprised at the time of filing more than ten claims.

- ☐ Only part of the claims have been paid within the prescribed time limit. The present European search report has been drawn up for the first ten claims and for those claims for which claims fees have been paid, namely claim(s):
- ☐ No claims fees have been paid within the prescribed time limit. The present European search report has been drawn up for the first ten claims.

LACK OF UNITY OF INVENTION

The Search Division considers that the present European patent application does not comply with the requirements of unity of invention and relates to several inventions or groups of inventions, namely:

see sheet B

- ☒ All further search fees have been paid within the fixed time limit. The present European search report has been drawn up for all claims.
- ☐ As all searchable claims could be searched without effort justifying an additional fee, the Search Division did not invite payment of any additional fee.
- ☐ Only part of the further search fees have been paid within the fixed time limit. The present European search report has been drawn up for those parts of the European patent application which relate to the inventions in respect of which search fees have been paid, namely claims:
- ☐ None of the further search fees have been paid within the fixed time limit. The present European search report has been drawn up for those parts of the European patent application which relate to the invention first mentioned in the claims, namely claims:



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 12 0481

DOCUMENTS CONSIDERED TO BE RELEVANT				
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)	
X	US 4 231 369 A (LARSEN HANS-OLE ET AL) 4 November 1980 (1980-11-04) * claims 16-19, 2.6.7 : column 6, line 29-32 ; column 8, line 26-34 ; column 9, line 2 * * column 4, line 30-44 *	1-5, 8, 9		
X	WO 99 11728 A (LIPMAN ROGER DAVID ARNOLD ; AVERY DENNISON CORP (US)) 11 March 1999 (1999-03-11) * claims 1-15 ; examples * * page 10, line 26 - page 11, line 28 *	1-5, 8, 9		
Y	JS 5 468 237 A (MILLER JOHN A ET AL) 21 November 1995 (1995-11-21) * abstract * * column 4, line 23-30 *	6, 7		
A	US 5 274 036 A (KORPMAN RALF ET AL) 28 December 1993 (1993-12-28) * abstract ; claims 1-15 *	1, 9		TECHNICAL FIELDS SEARCHED (Int.Cl.7)
A	JS 5 587 237 A (KORPMAN RALF ET AL) 24 December 1996 (1996-12-24) * abstract ; claims 1-3 *	1-9		
A	US 4 024 312 A (KORPMAN RALF) 17 May 1977 (1977-05-17) * claims 1-5 * * column 3, line 6-9 *	1-9		
The present search report has been drawn up for all claims				
Place of search		Date of completion of the search	Examiner	
THE HAGUE		16 January 2003	Hammond, A	
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background C : non-written disclosure P : intermediate document T : theory or principle underlying the invention L : earlier patent document, but published on or after the filing date D : document cited in the application C : document cited for other reasons A : member of the same patent family corresponding document				



European Patent
Office

LACK OF UNITY OF INVENTION
SHEET B

Application Number
EP 01 12 0481

The Search Division considers that the present European patent application does not comply with the requirements of unity of invention and relates to several inventions or groups of inventions, namely:

1. Claims: 1-4,8,9

A pressure-sensitive adhesive composition comprising : 100 parts wt. of a rubber component that is solid in an ordinary temperature ; 30 to 170 parts wt. of a rubber component that is liquid in an ordinary temperature ; and 50 to 400 parts wt. of a tackifier ; wherein the amount of the tackifier is 25 to 80 parts wt. based on 100 parts wt. of the total amount of the rubber components.

2. Claims: 5-7

A pressure-sensitive adhesive tape or sheet, comprising a pressure-sensitive adhesive composition according to claim 1 formed on one side of a backing film.

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 12 0481

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on:
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

16-01-2003

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
EP 0285181	A	05-10-1988	JP	2572763 B2	16-01-1997
			JP	63246327 A	13-10-1988
			EP	0285181 A2	05-10-1988
			US	4963361 A	16-10-1990
US 5760135	A	02-06-1998	US	5274036 A	28-12-1993
			AU	2660695 A	04-01-1996
			WO	9533794 A1	14-12-1995
			US	5587237 A	24-12-1996
			AT	184622 T	15-10-1999
			AU	678793 B2	12-06-1997
			AU	5607694 A	08-06-1994
			BR	9307453 A	01-06-1999
			DE	69326477 D1	21-10-1999
			DE	69326477 T2	03-02-2000
			EP	0670864 A1	13-09-1995
			JP	8506127 T	02-07-1996
			KR	187961 B1	01-06-1999
			NZ	258417 A	29-01-1997
			WO	9411437 A1	26-05-1994
EP 1043373	A	11-10-2000	JP	2000290609 A	17-10-2000
			EP	1043373 A2	11-10-2000
			US	6414073 B1	02-07-2002
DE 4207657	A	17-09-1992	DE	4207657 A1	17-09-1992
			JP	5105630 A	27-04-1993
US 4551490	A	05-11-1985	AT	36808 T	15-09-1988
			AU	578612 B2	03-11-1988
			AU	2950184 A	10-01-1985
			CA	1225764 A1	18-08-1987
			DD	223459 A5	12-06-1985
			DE	3473731 D1	06-10-1988
			DK	311384 A ,B,	28-12-1984
			EP	0130061 A1	02-01-1985
			ES	8602898 A1	16-03-1986
			IE	58125 B1	14-07-1993
			IL	72163 A	30-10-1987
			JP	1970283 C	18-09-1995
			JP	6078507 B	05-10-1994
			JP	60020976 A	02-02-1985
			NO	842584 A ,B,	28-12-1984
			NZ	208566 A	12-11-1986
			ZA	8404601 A	27-02-1985

EPC 1989/2:432

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 12 0481

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

16-01-2003

Patent document cited in search report		Publication date	Patent family members:	Publication date
US 4231369	A	04-11-1980	GB 1576522 A	08-10-1980
			AU 518743 B2	15-10-1981
			AU 3638878 A	29-11-1979
			CA 1124604 A1	01-06-1982
			DE 2822535 A1	07-12-1978
			DK 227578 A ,B	25-11-1978
			FR 2392076 A1	22-12-1978
			IT 1108607 B	09-12-1985
			JP 1440060 C	30-05-1988
			JP 54013693 A	01-02-1979
			JP 62047545 B	08-10-1987
			NL 7805643 A ,B	28-11-1978
			SE 438780 B	13-05-1985
			SE 7805869 A	25-11-1978
WO 9911728	A	11-03-1999	AU 735912 B2	19-07-2001
			AU 8349098 A	22-03-1999
			CA 2303276 A1	11-03-1999
			EP 1007597 A1	14-06-2000
			WO 9911728 A1	11-03-1999
			JP 2001515091 T	18-09-2001
US 5468237	A	21-11-1995	AU 652853 B2	08-09-1994
			AU 2307992 A	16-03-1993
			BR 9206381 A	27-12-1994
			CA 2109563 A1	04-03-1993
			DE 69208256 D1	21-03-1996
			DE 69208256 T2	27-06-1996
			EP 0599861 A1	08-06-1994
			ES 2083179 T3	01-04-1996
			JP 6510313 T	17-11-1994
			MX 9204542 A1	01-02-1993
			WO 9304135 A1	04-03-1993
US 5274036	A	28-12-1993	AT 184622 T	15-10-1999
			AU 678793 B2	12-06-1997
			AU 5607694 A	08-06-1994
			BR 9307453 A	01-06-1999
			DE 69326477 D1	21-10-1999
			DE 69326477 T2	03-02-2000
			EP 0670864 A1	13-09-1995
			JP 8506127 T	02-07-1996
			KR 187961 B1	01-06-1999
			NZ 758417 A	29-01-1997
			WO 9411437 A1	26-05-1994
			US 5760135 A	02-06-1998

SPC FORM 2-95

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 12 0481

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

16-01-2003

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5274036 A		US 5587237 A	24-12-1996
US 5587237 A	24-12-1996	US 5274036 A	28-12-1993
		US 5760135 A	02-06-1998
		AT 184622 T	15-10-1999
		AU 678793 B2	12-06-1997
		AU 5607694 A	08-06-1994
		BR 9307453 A	01-06-1999
		DE 69326477 D1	21-10-1999
		DE 69326477 T2	03-02-2000
		EP 0670864 A1	13-09-1995
		JP 8506127 T	02-07-1996
		KR 187961 B1	01-06-1999
		NZ 258417 A	29-01-1997
		WO 9411437 A1	26-05-1994
US 4024312 A	17-05-1977	AU 518205 B2	17-09-1981
		AU 2629277 A	04-01-1979
		BR 7704063 A	11-07-1978
		CA 1080559 A1	01-07-1980
		DE 2728346 A1	05-01-1978
		ES 459978 A1	01-12-1978
		FR 2355893 A1	20-01-1978
		GB 1559933 A	30-01-1980
		IT 1079059 B	08-05-1985
		JP 1305861 C	13-03-1986
		JP 53000235 A	05-01-1978
		JP 60031233 B	20-07-1985
		NL 7706854 A ,B,	28-12-1977
		NZ 184296 A	08-06-1979
		PH 13292 A	04-03-1980
		ZA 7703754 A	31-01-1979

For more details about this annex see Official Journal of the European Patent Office, No. 12/82